

Johnson Matthey Argo-braze 40N Silver Brazing Alloy for Tungsten Carbide Brazing

Category : Metal , Nonferrous Metal , Precious Metal , Silver Alloy , Solder/Braze Alloy

Material Notes:

An economical alloy for brazing tungsten carbides and stainless steels. Optimum Joint Gap 0.1 - 0.25 mm.AWS A5.8-92 BAg-4Federal Specification QQ-B-564 BAg-4Information provided by Johnson Matthey.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Johnson-Matthey-Argo-braze-40N-Silver-Brazing-Alloy-for-Tungsten-Carbide-Brazing.php

Thermal Properties	Metric	English	Comments
Melting Point	660 - 780 °C	1220 - 1440 °F	
Solidus	660 °C	1220 °F	
Liquidus	780 °C	1440 °F	

Component Elements Properties	Metric	English	Comments
Copper, Cu	30 %	30 %	
Nickel, Ni	2.0 %	2.0 %	
Silver, Ag	40 %	40 %	
Zinc, Zn	28 %	28 %	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China