

Johnson Matthey Argo-braze 49H Silver Brazing Alloy for Tungsten Carbide Brazing

Category : Metal , Nonferrous Metal , Precious Metal , Silver Alloy , Solder/Braze Alloy

Material Notes:

Optimum Joint Gap 0.1 - 0.25 mm.AWS A5.8-92 BAg-22BS EN 1044 1999 AG502Equivalent to Engelhard Silvaloy A-49NMEquivalent to Handy & Harman Braze 495Information provided by Johnson Matthey.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Johnson-Matthey-Argo-braze-49H-Silver-Brazing-Alloy-for-Tungsten-Carbide-Brazing.php

Thermal Properties	Metric	English	Comments
Melting Point	680 - 705 °C	1260 - 1300 °F	
Solidus	680 °C	1260 °F	
Liquidus	705 °C	1300 °F	

Component Elements Properties	Metric	English	Comments
Copper, Cu	16 %	16 %	
Manganese, Mn	7.5 %	7.5 %	
Nickel, Ni	4.5 %	4.5 %	
Silver, Ag	49 %	49 %	
Zinc, Zn	23 %	23 %	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China