

Johnson Matthey Copper-flo AWS Alloy for Fluxless Brazing of Copper

Category : Metal , Nonferrous Metal , Copper Alloy , Solder/Braze Alloy

Material Notes:

The copper-flo alloys are used for manufacture of heat exchanger return bends, refrigeration pipes and hot water cylinders. Optimum Joint Gap 0.75 - 0.2 mm. AWS A5.8-92 BCuP-2BS EN 1044 1999 CP202; Does not conform exactly to the requirements of EN 1044. Federal Specification QQ-B-650 BCuP-2 Equivalent to Engelhard Silvaloy 0 Equivalent to Handy & Harman Fos-Flo 7 Equivalent to J W Harris Harris O Information provided by Johnson Matthey.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Johnson-Matthey-Copper-flo-AWS-Alloy-for-Fluxless-Brazing-of-Copper.php

Thermal Properties	Metric	English	Comments
Melting Point	710 - 795 Â°C	1310 - 1460 Â°F	
Solidus	710 Â°C	1310 Â°F	
Liquidus	795 Â°C	1460 Â°F	

Component Elements Properties	Metric	English	Comments
Copper, Cu	92.75 %	92.75 %	
Phosphorous, P	7.25 %	7.25 %	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China