

## Johnson Matthey Matti-sil 30 Cadmium Free Brazing Alloy

Category : Metal , Nonferrous Metal , Copper Alloy , Precious Metal , Silver Alloy , Solder/Braze Alloy

### Material Notes:

The wide melting range of Matti-sil 30 makes it suitable for filling larger joint gaps and producing fillets where desired. Optimum Joint Gap 0.075 - 0.2 mm. AWS A5.8-92 BAg-20 Federal Specification QQ-B-564 BAg-20 Equivalent to Engelhard Silvaloy A-30 Equivalent to Handy & Harman Braze 300 Equivalent to J W Harris Safety-Silv 30 Information provided by Johnson Matthey.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Johnson-Matthey-Matti-sil-30-Cadmium-Free-Brazing-Alloy.php](http://www.lookpolymers.com/polymer_Johnson-Matthey-Matti-sil-30-Cadmium-Free-Brazing-Alloy.php)

Thermal Properties	Metric	English	Comments
Melting Point	675 - 765 Â°C	1250 - 1410 Â°F	
Solidus	675 Â°C	1250 Â°F	
Liquidus	765 Â°C	1410 Â°F	

Component Elements Properties	Metric	English	Comments
Copper, Cu	38 %	38 %	
Silver, Ag	30 %	30 %	
Zinc, Zn	32 %	32 %	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China