

Johnson Matthey Matti-sil 38Sn Cadmium Free Brazing Alloy

Category : Metal , Nonferrous Metal , Precious Metal , Silver Alloy , Solder/Braze Alloy

Material Notes:

An economic alternative to Matti-sil 40Sn with similar properties. Optimum Joint Gap 0.075 - 0.2 mm. AMS 4761AWS A5.8-92 BAg-34 Equivalent to Engelhard Silvaloy A-38T Equivalent to Handy & Harman Braze 380 Equivalent to J W Harris Safety-Silv 38 Information provided by Johnson Matthey.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Johnson-Matthey-Matti-sil-38Sn-Cadmium-Free-Brazing-Alloy.php

Thermal Properties	Metric	English	Comments
Melting Point	660 - 720 °C	1220 - 1330 °F	
Solidus	660 °C	1220 °F	
Liquidus	720 °C	1330 °F	

Component Elements Properties	Metric	English	Comments
Copper, Cu	32 %	32 %	
Silver, Ag	38 %	38 %	
Tin, Sn	2.0 %	2.0 %	
Zinc, Zn	28 %	28 %	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China