

Johnson Matthey Matti-sil 45 Cadmium Free Brazing Alloy

Category : Metal , Nonferrous Metal , Precious Metal , Silver Alloy , Solder/Braze Alloy

Material Notes:

A medium flowing alloy which is often used for marine and Shipbuilding applications. Optimum Joint Gap 0.075 - 0.2 mm. AWS A5.8-92 BAg-5BS EN 1044 1999 AG203 Federal Specification QQ-B-564 BAg-5 Equivalent to Engelhard Silvaloy A-45 Equivalent to Handy & Harman Braze 450 Equivalent to J W Harris Safety-Silv 45 Information provided by Johnson Matthey.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Johnson-Matthey-Matti-sil-45-Cadmium-Free-Brazing-Alloy.php

Thermal Properties	Metric	English	Comments
Melting Point	675 - 735 Â°C	1250 - 1360 Â°F	
Solidus	675 Â°C	1250 Â°F	
Liquidus	735 Â°C	1360 Â°F	

Component Elements Properties	Metric	English	Comments
Copper, Cu	30 %	30 %	
Silver, Ag	45 %	45 %	
Zinc, Zn	25 %	25 %	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China