

Johnson Matthey Matti-sil 56Sn Cadmium Free Brazing Alloy

Category : Metal , Nonferrous Metal , Precious Metal , Silver Alloy , Solder/Braze Alloy

Material Notes:

A very free flowing alloy which is widely used throughout the World for its low melting point and short melting range. Optimum Joint Gap 0.05 - 0.15 mm. AMS 4763 AWS A5.8-92 BAg-7 BS EN 1044 1999 AG102 Federal Specification QQ-B-564 BAg-7 Equivalent to Engelhard Silvaloy A-56T Equivalent to Handy & Harman Braze 560 Equivalent to J W Harris Safety-Silv 56 Information provided by Johnson Matthey.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Johnson-Matthey-Matti-sil-56Sn-Cadmium-Free-Brazing-Alloy.php

Thermal Properties	Metric	English	Comments
Melting Point	618 - 652 Â°C	1140 - 1210 Â°F	
Solidus	618 Â°C	1140 Â°F	
Liquidus	652 Â°C	1210 Â°F	

Component Elements Properties	Metric	English	Comments
Copper, Cu	22 %	22 %	
Silver, Ag	56 %	56 %	
Tin, Sn	5.0 %	5.0 %	
Zinc, Zn	17 %	17 %	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China