

Johnson Matthey Mattibraise 35 Cadmium Containing Silver Brazing Alloy

Category : Metal , Nonferrous Metal , Precious Metal , Silver Alloy , Solder/Braze Alloy

Material Notes:

A free flowing alloy suitable for larger joint clearances and forming fillets. Safety Precautions with Cadmium Containing Alloys: Today the potential danger from cadmium fume is widely recognized. The localized extraction of fumes during brazing is now virtually obligatory. The use of cadmium containing alloys is not permitted in the manufacture of food and drink handling equipment and medical instruments. If cadmium containing alloys are felt likely to cause a health hazard then use a cadmium free alloy from the Johnson Matthey Matti-sil range. Full details on exposure levels (OES) are given in the specific Material Safety Data Sheets. These should always be consulted before use of a cadmium bearing brazing alloy. Optimum Joint Gap 0.075 - 0.2 mm. AMS 4768AWS A5.8-92 BAg-2 Federal Specification QQ-B-564 VIII Equivalent to Engelhard Silvaloy 35 Equivalent to Handy & Harman Easy-flo 35 Information provided by Johnson Matthey.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Johnson-Matthey-Mattibraise-35-Cadmium-Containing-Silver-Brazing-Alloy.php

Thermal Properties	Metric	English	Comments
Melting Point	605 - 700 Â°C	1120 - 1290 Â°F	
Solidus	605 Â°C	1120 Â°F	
Liquidus	700 Â°C	1290 Â°F	

Component Elements Properties	Metric	English	Comments
Cadmium, Cd	18 %	18 %	
Copper, Cu	26 %	26 %	
Silver, Ag	35 %	35 %	
Zinc, Zn	21 %	21 %	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China