

KB Alloys 6% Zirconium Aluminum Alloy

Category : Metal , Nonferrous Metal , Aluminum Alloy

Material Notes:

Many of the disadvantages of using elemental hardener additions can be overcome by using aluminum base master alloys. When aluminum base master alloys are made with a high melting temperature element, the melting temperature of the master alloy, even at high concentrations, is significantly reduced from that of the element. Use of master alloys with rapid solution rates also means shorter furnace cycles and thus increased throughput and better furnace utilization. Reduced furnace temperature and shorter furnace cycles improve recovery of the alloying element from the master alloy, and improve precision of the desired alloy composition. Information provided by KB AlloysAl. Assoc. Registration No: H2606

Order this product through the following link:

http://www.lookpolymers.com/polymer_KB-Alloys-6-Zirconium-Aluminum-Alloy.php

Component Elements Properties	Metric	English	Comments
Aluminum, Al	92.87 - 93.87 %	92.87 - 93.87 %	
Iron, Fe	0.25 %	0.25 %	
Other, each	0.030 %	0.030 %	
Other, total	0.10 %	0.10 %	
Silicon, Si	0.20 %	0.20 %	
Titanium, Ti	0.050 %	0.050 %	
Zirconium, Zr	5.5 - 6.5 %	5.5 - 6.5 %	

Descriptive Properties	Value	Comments
Form	Waffle Ingot	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China