

KKPC KOSYN 1724 Styrene Butadiene Rubber

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE)

Material Notes:

Styrene Butadiene RubberCharacteristics: KOSYN SBR, a useful synthetic rubber, is a copolymer made from butadiene and styrene by cold emulsion polymerization. It has superior abrasion resistance and heat resistance in comparison with natural rubber, as well as widely useful physical properties of easy vulcanization and stable scorch properties. The products of KOSYN SBR are classified according to the emulsifying agent and stabilizer used in manufacturing process.Applications: Tires, footwear, rubber hose, auto equipment and other rubber products for industrial use.Additional Notes: Bound Styrene: 40%Extender Oil: 50; AromaticStabilizer: StainingEmulsifier: Mixed soap of rosin acid and fatty acidCoagulant: Salt-AcidCompound Properties: SRB 100, ZnO 3, S/A 1, HAF Black (IRB#7) 50, Accelerator TBBS1, Sulfur 1.75, Total: 156.75Vulcanization: 145Â°C *35 m., Press VulcanizationThis product is so sensitive to sunlight and humidity that it can be tarnished and caused deterioration of quality if exposed. It is recommended to store it in cool and shady area lest it should be exposed to direct sunlight. Do not expose to incompatible materials or contaminants.Data provided by Korea Kumho Petrochemical Co., Ltd.

Order this product through the following link:
http://www.lookpolymers.com/polymer_KKPC-KOSYN-1724-Styrene-Butadiene-Rubber.php

Physical Properties	Metric	English	Comments
Density	0.970 g/cc	0.0350 lb/inÂ³	Not Compounded
Mooney Viscosity	53	53	Raw; ML1+4
	@Temperature 100 Â°C	@Temperature 212 Â°F	
	60	60	Compounded; ML1+4
	@Temperature 100 Â°C	@Temperature 212 Â°F	

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	66	66	Vulcanized
Tensile Strength, Ultimate	22.8 MPa	3300 psi	Vulcanized
Elongation at Break	560 %	560 %	Vulcanized
300% Modulus	0.0103 GPa	1.49 ksi	Vulcanized
Rebound	24 %	24 %	ASTM Test, Vulcanized
Flex Crack Resistance	15000	15000	145Â°C / 35 min., Press Vulcanization
Tear Strength	43.1 kN/m	246 pli	B-type, Vulcanized
Abrasion	0.17	0.17	De Mattia Flexometer: Cut Growth 2mm --> 15mm, Flexes
Compression Set	50 %	50 %	70 hrs, 25% def, Vulcanized

Mechanical Properties	@Temperature 100 Å°C Metric	@Temperature 212 Å°F English	Comments
-----------------------	--------------------------------	---------------------------------	----------

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com
Tel : +86 021-51131842
Mobile : +86 13061808058
Skype : lookpolymers
Address : United North Road 215,Fengxian District, Shanghai City,China