

KKPC KOSYN KNB 35LL Acrylonitrile Butadiene Rubber (NBR)

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE)

Material Notes:

Acrylonitrile Butadiene Rubber (NBR) Characteristics: KOSYN KNB is copolymer of high oil resistance and chemical resistance made from acrylonitrile and butadiene by the cold emulsion polymerization. Our NBR has superior working properties such as roll winding properties, compounding dispersibility and extrusion properties. Also, it is easily processed on account of the excellent vulcanization properties. **Applications:** General oil-resistant Rubber Products such as packing, gasket, hose, rolls, and shoe soles **Additional Notes:** Bound Acrylonitrile: 34% **Compound Properties:** NBR 100, ZnO 3, Stearic Acid 1, HAF Black (IRB#7) 40, Accelerator TBBS 1, Sulfur 1.5, Total: 146.5 **Volume Change:** -1% This product is so sensitive to sunlight and humidity that it can be tarnished and caused deterioration of quality if exposed. It is recommended to store it in cool and shady area lest it should be exposed to direct sunlight. Do not expose to incompatible materials or contaminants. Data provided by Korea Kumho Petrochemical Co., Ltd.

Order this product through the following link:

http://www.lookpolymers.com/polymer_KKPC-KOSYN-KNB-35LL-Acrylonitrile-Butadiene-Rubber-NBR.php

Physical Properties	Metric	English	Comments
Density	0.940 g/cc	0.0340 lb/in ³	Not Compounded
Mooney Viscosity	33	33	Raw; ML1+4
	@Temperature 100 Â°C	@Temperature 212 Â°F	
	58	58	Compounded; ML1+4
	@Temperature 100 Â°C	@Temperature 212 Â°F	

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	73	73	150Â°C, 40 min., Pressure Vulcanization. 0% Change after 100Â°C, 70 hrs, Oil Immersion
Tensile Strength, Ultimate	29.4 MPa	4270 psi	150Â°C, 40 min., Pressure Vulcanization. -8% Change after 100Â°C, 70 hrs, Oil Immersion
Elongation at Break	590 %	590 %	150Â°C, 40 min., Pressure Vulcanization. -29% Change after 100Â°C, 70 hrs, Oil Immersion
300% Modulus	0.0127 GPa	1.85 ksi	150Â°C, 40 min., Pressure Vulcanization. 42% Change after 100Â°C, 70 hrs, Oil Immersion

Thermal Properties	Metric	English	Comments
Shrinkage	0.000 %	0.000 %	after Oil Immersion
	@Time 252000 sec	@Time 70.0 hour	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China