## KKPC KOSYN KTR 302 Thermoplastic Elastomer (TPE)

Category : Polymer , Thermoplastic , Elastomer, TPE , Styrenic TPE

## Material Notes:

Thermoplastic Elastomer (TPE)Characteristics: KOSYN KTR101 is linear block copolymer made by solution polymerization which polymerizes butadiene and styrene in organic solvent. It is thermoplastics free of vulcanization and has superior tensile strength and elasticity.Applications: Asphalt roofing, waterproof agent, modifier and adhesives.Additional Notes: Bound Styrene: 46%Volatile Matter: 0.7%; ASTM D1416This product is so sensitive to sunlight and humidity that it can be tarnished and caused deterioration of quality if exposed. It is recommended to store it in cool and shady area lest it should be exposed to direct sunlight. Do not expose to incompatible materials or contaminants.Data provided by Korea Kumho Petrochemical Co., Ltd.

## Order this product through the following link:

http://www.lookpolymers.com/polymer\_KKPC-KOSYN-KTR-302-Thermoplastic-Elastomer-TPE.php

| Physical Properties | Metric                               | English                              | Comments   |
|---------------------|--------------------------------------|--------------------------------------|------------|
| Density             | 0.940 g/cc                           | 0.0340 lb/in³                        | ISO 2781   |
| Melt Flow           | 10.5 g/10 min                        | 10.5 g/10 min                        | ASTM D1238 |
|                     | @Load 5.00 kg,<br>Temperature 200 °C | @Load 11.0 lb,<br>Temperature 392 °F |            |

| Mechanical Properties      | Metric     | English  | Comments          |
|----------------------------|------------|----------|-------------------|
| Hardness, Shore A          | 73         | 73       | 5 sec; ASTM D2240 |
| Tensile Strength, Ultimate | 18.0 MPa   | 2610 psi | ASTM D412         |
| Elongation at Break        | 900 %      | 900 %    | ASTM D412         |
| Modulus of Elasticity      | 0.0180 GPa | 2.61 ksi | ASTM D412         |

## Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com Email : sales@lookpolymers.com Tel : +86 021-51131842 Mobile : +86 13061808058 Skype : lookpolymers Address : United North Road 215,Fengxian District, Shanghai City,China