

KKPC KOSYN SOL 5990 Solution Styrene Butadiene Rubber (S-SBR)

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE)

Material Notes:

Solution Styrene Butadiene Rubber (S-SBR) Characteristics: This product is made by solution polymerization under which styrene and butadiene react in organic solvent using alkyl-lithium catalyst. It is superior to SBR, which is made by emulsion polymerization, in processability, visco-elasticity and low temperature properties. Also, the products' properties can be adjusted to the purpose of consumption according to the proper proportion of styrene content, the micro structure and the molecular weight. **Applications:** Shoes, Soles, Tires, Machine Parts, Energy-saving Tires, High-efficiency Tires **Additional Notes:** Bound Styrene: 5% cis-1,4 Contents: 7.5% trans-1,4 Contents: 12.5% Vinyl Contents: 80% **Dynamic Test:** GABO Qualimeter (11Hz)(TAN) 0Â°C: 0.612 10Â°C: 0.384 60Â°C: 0.103 70Â°C: 0.1 This product is so sensitive to sunlight and humidity that it can be tarnished and caused deterioration of quality if exposed. It is recommended to store it in cool and shady area lest it should be exposed to direct sunlight. Do not expose to incompatible materials or contaminants. Data provided by Korea Kumho Petrochemical Co., Ltd.

Order this product through the following link:

http://www.lookpolymers.com/polymer_KKPC-KOSYN-SOL-5990-Solution-Styrene-Butadiene-Rubber-S-SBR.php

Physical Properties	Metric	English	Comments
Mooney Viscosity	65	65	Raw; ML1+4
	@Temperature 100 Â°C	@Temperature 212 Â°F	
	95.6	95.6	ML1+4; Polymer 100, HAF Black (IRB#6) 50, ZnO 3, Stearic Acid 1, D 0.3, DM 0.6, Sulfur 1.75, Total: 156.65, Cure: 145Â°C, 35 minutes.
	@Temperature 100 Â°C	@Temperature 212 Â°F	

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	63	63	JIS-A
Tensile Strength, Ultimate	22.8 MPa	3300 psi	
Elongation at Break	440 %	440 %	
300% Modulus	0.0132 GPa	1.92 ksi	

Thermal Properties	Metric	English	Comments
Glass Transition Temp, Tg	-17.0 Â°C	1.40 Â°F	Compound

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China