

KKPC Kuhmo GP 150 High Heat Resistant, High Rigidity GPPS

Category : Polymer , Thermoplastic , Polystyrene (PS) , Polystyrene, Heat Resistant Grade

Material Notes:

Key features: High Heat-resistance, High Strength Common Uses: Vegetable boxes in refrigerators, humidifiers, lighting apparatus, cassette tape cases, parts of optical instruments, PS paper, etc.GPPS has excellent transparence, colorability, electric property, water-resistance, harmlessness, molding processability, and stability of dimension.Data provided by Korea Kumho Petrochemical Co., Ltd.

Order this product through the following link:

http://www.lookpolymers.com/polymer_KKPC-Kuhmo-GP-150-High-Heat-Resistant-High-Rigidity-GPPS.php

Physical Properties	Metric	English	Comments
Density	1.04 g/cc	0.0376 lb/in ³	ASTM D792
Water Absorption	0.030 %	0.030 %	24 hr immersion; ASTM D570
Linear Mold Shrinkage	0.0030 - 0.0060 cm/cm	0.0030 - 0.0060 in/in	ASTM D955
Melt Flow	4.5 g/10 min	4.5 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	75	75	ASTM D785
Tensile Strength, Ultimate	51.9 MPa	7520 psi	ASTM D638
Elongation at Break	2.5 %	2.5 %	ASTM D638
Flexural Yield Strength	98.423 MPa	14275 psi	ASTM D790
Flexural Modulus	2.986 GPa	433.1 ksi	ASTM D790
Izod Impact, Notched	0.246 J/cm @Thickness 3.20 mm	0.460 ft-lb/in @Thickness 0.126 in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	87.0 Å°C	189 Å°F	unannealed; ASTM D648
Vicat Softening Point	105 Å°C	221 Å°F	ASTM D1525
Flammability, UL94	HB	HB	
	@Thickness 1.60 mm	@Thickness 0.0630 in	
	HB	HB	
	@Thickness 2.20 mm	@Thickness 0.0866 in	
	HB	HB	

Thermal Properties	Metric @ Thickness 3.20 mm	English @ Thickness 0.126 in	Comments
Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+16 ohm-cm	1.00e+16 ohm-cm	ASTM D257
Dielectric Strength	21.7 kV/mm	550 kV/in	ASTM D149

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China