

Karina 02/284-FC-LMP Yellow Color Concentrate for PVC

Category : Other Engineering Material , Additive/Filler for Polymer , Polymer , Thermoplastic

Material Notes:

Information provided by Karina Indústria e Comércio de Plásticos Ltda.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Karina-02284-FC-LMP-Yellow-Color-Concentrate-for-PVC.php

| Physical Properties | Metric | English | Comments |
|---------------------|------------------|------------------|----------------------|
| Specific Gravity | 1.47 - 1.53 g/cc | 1.47 - 1.53 g/cc | NBR NM-IEC 60811-1-3 |
| ASTM Color | 15.61 - 18.61 | 15.61 - 18.61 | Color A, ME 12 |
| | 71.4 - 74.4 | 71.4 - 74.4 | Color B, ME 12 |
| | 76.25 - 79.25 | 76.25 - 79.25 | Color L, ME 12 |

| Mechanical Properties | Metric | English | Comments |
|-----------------------|----------------|--------------------|----------|
| Hardness, Shore A | 78 - 82 | 78 - 82 | NBR 7456 |
| | @Time 15.0 sec | @Time 0.00417 hour | |

| Component Elements Properties | Metric | English | Comments |
|-------------------------------|-------------|-------------|-----------|
| Cadmium, Cd | <= 0.0050 % | <= 0.0050 % | IEC 62321 |
| Chromium, Cr | <= 0.010 % | <= 0.010 % | IEC 62321 |
| Lead, Pb | <= 0.010 % | <= 0.010 % | IEC 62321 |
| Mercury, Hg | <= 0.010 % | <= 0.010 % | IEC 62321 |

| Electrical Properties | Metric | English | Comments |
|-----------------------|--------------------|--------------------|----------|
| Volume Resistivity | >= 1.00e+14 ohm-cm | >= 1.00e+14 ohm-cm | NBR 5403 |

| Descriptive Properties | Value | Comments |
|------------------------|-----------|-----------|
| Application | Extrusion | |
| Bromine, Br (%) | < 0.01 | IEC 62321 |

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China