

## Karina 6122/23-RTR Kariprene Crepe

Category : Polymer , Thermoplastic

**Material Notes:**

Thermoplastic rubber compound recommended for injection of footwear soles. Information provided by Karina Indústria e Comércio de Plásticos Ltda.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Karina-612223-RTR-Kariprene-Crepe.php](http://www.lookpolymers.com/polymer_Karina-612223-RTR-Kariprene-Crepe.php)

Physical Properties	Metric	English	Comments
Density	0.900 - 0.960 g/cc	0.0325 - 0.0347 lb/in <sup>3</sup>	ASTM D 792

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	58 - 62	58 - 62	ASTM D 2240
	@Time 15.0 sec	@Time 0.00417 hour	
	62	62	After Injection Molding; ASTM D 2240
	@Time 15.0 sec	@Time 0.00417 hour	
Tensile Strength	>= 4.90 MPa	>= 711 psi	ASTM D 638
Elongation at Break	>= 450 %	>= 450 %	ASTM D 638
Abrasion	<= 220	<= 220	mm <sup>3</sup> ; DIN 53516

## Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China