

## Karina 802-10/55-AY-ERYB White PVC Compound

Category : Polymer , Thermoplastic , Vinyl (PVC) , PVC, Extruded

**Material Notes:**

Information provided by Karina Indústria e Comércio de Plásticos Ltda.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Karina-802-1055-AY-ERYB-White-PVC-Compound.php](http://www.lookpolymers.com/polymer_Karina-802-1055-AY-ERYB-White-PVC-Compound.php)

| Physical Properties | Metric           | English          | Comments       |
|---------------------|------------------|------------------|----------------|
| Specific Gravity    | 1.47 - 1.53 g/cc | 1.47 - 1.53 g/cc | NBR 14288      |
| ASTM Color          | -2.11 - 0.89     | -2.11 - 0.89     | Color A, ME 12 |
|                     | 0.56 - 3.56      | 0.56 - 3.56      | Color B, ME 12 |
|                     | 87.74 - 90.74    | 87.74 - 90.74    | Color L, ME 12 |

| Mechanical Properties | Metric         | English            | Comments    |
|-----------------------|----------------|--------------------|-------------|
| Hardness, Shore D     | 78 - 82        | 78 - 82            | ASTM D 2240 |
|                       | @Time 15.0 sec | @Time 0.00417 hour |             |
| Tensile Strength      | >= 39.2 MPa    | >= 5690 psi        | ASTM D 638  |

| Thermal Properties    | Metric     | English   | Comments   |
|-----------------------|------------|-----------|------------|
| Vicat Softening Point | >= 78.0 °C | >= 172 °F | ASTM D 638 |

| Descriptive Properties | Value                    | Comments |
|------------------------|--------------------------|----------|
| Application            | General Purpose Profiles |          |

## Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China