

## Karina E 843-18/302-CRM Gray PVC Compound

Category : Polymer , Thermoplastic , Vinyl (PVC)

**Material Notes:**

Information provided by Karina Indústria e Comércio de Plásticos Ltda.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Karina-E-843-18302-CRM-Gray-PVC-Compound.php](http://www.lookpolymers.com/polymer_Karina-E-843-18302-CRM-Gray-PVC-Compound.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.33 - 1.39 g/cc	1.33 - 1.39 g/cc	ASTM D 792
ASTM Color	-4.63 - -1.63	-4.63 - -1.63	Color B, ME 12
	-2.13 - 0.87	-2.13 - 0.87	Color A, ME 12
	37.38 - 40.38	37.38 - 40.38	Color L, ME 12

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	78 - 82	78 - 82	ASTM D 2240
	@Time 15.0 sec	@Time 0.00417 hour	
Tensile Strength	>= 34.3 MPa	>= 4980 psi	ASTM D 638

Thermal Properties	Metric	English	Comments
Vicat Softening Point	>= 67.0 °C	>= 153 °F	ASTM D 1525

Descriptive Properties	Value	Comments
Application	Fittings	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China