

Karina E 854-35/9-A-ERYB Ivory PVC Compound

Category : Polymer , Thermoplastic , Vinyl (PVC) , PVC, Extruded

Material Notes:

Information provided by Karina Indústria e Comércio de Plásticos Ltda.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Karina-E-854-359-A-ERYB-Ivory-PVC-Compound.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.37 - 1.43 g/cc	1.37 - 1.43 g/cc	ASTM D 792
ASTM Color	-2.54 - -0.940	-2.54 - -0.940	Color A, ME 12
	6.21 - 7.81	6.21 - 7.81	Color B, ME 12
	87.89 - 89.49	87.89 - 89.49	Color L, ME 12

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	75 - 79 @Time 15.0 sec	75 - 79 @Time 0.00417 hour	ASTM D 2240
Tensile Strength	>= 45.8 MPa	>= 6640 psi	ASTM D 638
Izod Impact, Notched	>= 0.667 J/cm	>= 1.25 ft-lb/in	Method A; ASTM D 256

Thermal Properties	Metric	English	Comments
Vicat Softening Point	>= 75.0 Â°C	>= 167 Â°F	ASTM D 1525
Heat Distortion Temperature	>= 65.0 Â°C	>= 149 Â°F	ASTM D 648
Flammability, UL94	V-0	V-0	

Descriptive Properties	Value	Comments
Application	General Purpose Profiles	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China