

## Karina E 858-10/16-ERYA PVC Compound

Category : Polymer , Thermoplastic , Vinyl (PVC) , PVC, Extruded

**Material Notes:**

Information provided by Karina Indústria e Comércio de Plásticos Ltda.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Karina-E-858-1016-ERYA-PVC-Compound.php](http://www.lookpolymers.com/polymer_Karina-E-858-1016-ERYA-PVC-Compound.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.27 - 1.33 g/cc	1.27 - 1.33 g/cc	ASTM D 792
ASTM Color	-3.99 - -0.990	-3.99 - -0.990	Color A, ME 12
	6.1 - 9.1	6.1 - 9.1	Color B, ME 12
	80.78 - 83.78	80.78 - 83.78	Color L, ME 12

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	78 - 82	78 - 82	ASTM D 2240
	@Time 15.0 sec	@Time 0.00417 hour	
Tensile Strength	>= 34.3 MPa	>= 4980 psi	ASTM D 638
Izod Impact, Notched	>= 0.179 J/cm	>= 0.335 ft-lb/in	Method A; ASTM D 256
	>= 0.583 J/cm	>= 1.09 ft-lb/in	Reversed Notch (Method E); ASTM D 256

Thermal Properties	Metric	English	Comments
Vicat Softening Point	>= 72.8 Å°C	>= 163 Å°F	ASTM D 1525

Descriptive Properties	Value	Comments
Application	General Purpose Profiles	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China