

## Kazanorgsintez PC-007 Polycarbonate

Category : Polymer , Thermoplastic , Polycarbonate (PC)

### Material Notes:

Production Method: Obtained by means of polycondensation method. Application: Intended for product manufacture by method of extrusion and die-casting. Information Provided by Kazanorgsintez

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Kazanorgsintez-PC-007-Polycarbonate.php](http://www.lookpolymers.com/polymer_Kazanorgsintez-PC-007-Polycarbonate.php)

Physical Properties	Metric	English	Comments
Melt Flow	6.0 - 8.0 g/10 min	6.0 - 8.0 g/10 min	
	@Load 1.20 kg, Temperature 300 Å°C	@Load 2.65 lb, Temperature 572 Å°F	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	>= 55.0 MPa	>= 7980 psi	2nd Grade
	>= 58.0 MPa	>= 8410 psi	1st Grade
	>= 60.0 MPa	>= 8700 psi	Superior Quality
Elongation at Break	>= 80 %	>= 80 %	2nd Grade
	>= 100 %	>= 100 %	Superior Quality, 1st Grade
Flexural Modulus	2.00 GPa	290 ksi	2nd Grade
	2.25 GPa	326 ksi	Superior Grade, 1st Grade
Transverse Strength	>= 70.0 MPa	>= 10200 psi	2nd Grade, at max sample load
	>= 80.0 MPa	>= 11600 psi	Superior Quality, 1st Grade, at max sample load
Compressive Yield Strength	>= 70.0 MPa	>= 10200 psi	
Izod Impact, Unnotched (ISO)	60.0 kJ/mÅ²	28.6 ft-lb/inÅ²	2nd Grade
	66.0 kJ/mÅ²	31.4 ft-lb/inÅ²	Superior Grade, 1st Grade

Thermal Properties	Metric	English	Comments
Vicat Softening Point	>= 147 Å°C	>= 297 Å°F	

Optical Properties	Metric	English	Comments
Transmission, Visible	85 %	85 %	2nd Grade

Optical Properties	89 % Metric	89 % English	Superior Quality, 1st Grade Comments
	>= 90 %	>= 90 %	Superior Grade, 1st Grade

Electrical Properties	Metric	English	Comments
Dielectric Constant	<= 3.1 @Frequency 1000 Hz	<= 3.1 @Frequency 1000 Hz	Superior Quality
Dielectric Strength	>= 20.0 kV/mm	>= 508 kV/in	Superior Quality
Dissipation Factor	<= 0.0090 @Frequency 1000 Hz	<= 0.0090 @Frequency 1000 Hz	Superior Quality

Descriptive Properties	Value	Comments
Amount of impurities [pcs]	10	1st Grade
	5	Superior Quality
Turbidity	0.8	Superior Grade, 1st Grade
	1	2nd Grade

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China