

## Kazanorgsintez PC-075DA Polycarbonate

Category: Polymer, Thermoplastic, Polycarbonate (PC)

## **Material Notes:**

Production Method: Obtained by means of polycondensation method. Application: Intended for manufacture of optical products by method of die-casting (including CD, DVD, and other discs), as well as the manufacture of mixed composites with other plastics. Information Provided by Kazanorgsintez

## Order this product through the following link:

http://www.lookpolymers.com/polymer\_Kazanorgsintez-PC-075DA-Polycarbonate.php

Physical Properties	Metric	English	Comments
Melt Flow	5.3 - 10.3 g/10 min	5.3 - 10.3 g/10 min	
	@Load 1.20 kg, Temperature 250 °C	@Load 2.65 lb, Temperature 482 °F	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	>= 60.0 MPa	>= 8700 psi	
Elongation at Break	>= 50 %	>= 50 %	
Flexural Modulus	2.25 GPa	326 ksi	
Transverse Strength	>= 90.0 MPa	>= 13100 psi	at max sample load

Optical Properties	Metric	English	Comments	
Yellow Index	<= 3.5 %	<= 3.5 %		
Transmission, Visible	>= 89 %	>= 89 %		
	>= 90 %	>= 90 %		

## Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China