

## Kazanorgsintez PE2NT 15-5 Linear Low Density Polyethylene

Category : Polymer , Thermoplastic , Polyethylene (PE) , LLDPE , Linear Low Density Polyethylene (LLDPE), Film Grade

**Material Notes:**

Production Method: Gaseous-phase method. Application: Composition is intended to be processed into a stretch film. Information Provided by Kazanorgsintez

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Kazanorgsintez-PE2NT-15-5-Linear-Low-Density-Polyethylene.php](http://www.lookpolymers.com/polymer_Kazanorgsintez-PE2NT-15-5-Linear-Low-Density-Polyethylene.php)

Physical Properties	Metric	English	Comments
Density	0.918 - 0.923 g/cc	0.0332 - 0.0333 lb/in <sup>3</sup>	
	@Temperature 23.0 Å°C	@Temperature 73.4 Å°F	
Melt Flow	0.920 - 0.925 g/cc	0.0332 - 0.0334 lb/in <sup>3</sup>	
	@Temperature 20.0 Å°C	@Temperature 68.0 Å°F	
Melt Flow	0.70 - 1.2 g/10 min	0.70 - 1.2 g/10 min	Å±10%
	@Load 2.16 kg, Temperature 190 Å°C	@Load 4.76 lb, Temperature 374 Å°F	
Melt Flow	14 - 42 g/10 min	14 - 42 g/10 min	
	@Load 21.6 kg, Temperature 190 Å°C	@Load 47.6 lb, Temperature 374 Å°F	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	>= 9.00 MPa	>= 1310 psi	
Elongation at Break	>= 700 %	>= 700 %	
Tear Strength Test	>= 22	>= 22	MPa

Descriptive Properties	Value	Comments
Amount of impurities [pcs]	8	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China