

Kennametal Stellite Stellite® 12 PM cast

Category : Metal , Nonferrous Metal , Cobalt Alloy , Superalloy

Material Notes:

Applications: include vane plugs, fuel metering pins, spacer bushings, ball blanks (bearings), race blanks (bearings), diesel engine exhaust, fluid valve seats, saw cutter inserts, miscellaneous wear parts. Data provided by the manufacturer, Deloro Stellite Inc. Product of former Deloro Stellite Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Kennametal-Stellite-Stellite-12-PM-cast.php

Physical Properties	Metric	English	Comments
Density	8.52 g/cc	0.308 lb/in ³	theoretical

Mechanical Properties	Metric	English	Comments
Hardness, Brinell	394	394	Converted from Rockwell C hardness.
Hardness, Knoop	473	473	Converted from Rockwell C hardness.
Hardness, Rockwell A	72	72	Converted from Rockwell C hardness.
Hardness, Rockwell B	113	113	Converted from Rockwell C hardness. Beyond normal Rockwell B range, for comparison only.
Hardness, Rockwell C	43	43	Hot hardness.
Hardness, Vickers	416	416	Converted from Rockwell C hardness.

Thermal Properties	Metric	English	Comments
CTE, linear	11.9 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$	6.61 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$	
	@Temperature 0.000 - 100 $\text{Å}^\circ\text{C}$	@Temperature 32.0 - 212 $\text{Å}^\circ\text{F}$	
	12.8 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$	7.11 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$	
	@Temperature 0.000 - 200 $\text{Å}^\circ\text{C}$	@Temperature 32.0 - 392 $\text{Å}^\circ\text{F}$	
	12.9 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$	7.17 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$	
@Temperature 0.000 - 300 $\text{Å}^\circ\text{C}$	@Temperature 32.0 - 572 $\text{Å}^\circ\text{F}$		
13.4 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$	7.44 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$		
@Temperature 0.000 - 400 $\text{Å}^\circ\text{C}$	@Temperature 32.0 - 752 $\text{Å}^\circ\text{F}$		
13.8 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$	7.67 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$		

Thermal Properties	Metric @Temperature 0.000 - 300 Â°C	English @Temperature 32.0 - 539 Â°F	Comments
	14.1 Âµm/m-Â°C	7.83 Âµin/in-Â°F	
	@Temperature 0.000 - 600 Â°C	@Temperature 32.0 - 1110 Â°F	
	14.4 Âµm/m-Â°C	8.00 Âµin/in-Â°F	
	@Temperature 0.000 - 700 Â°C	@Temperature 32.0 - 1290 Â°F	
	15.2 Âµm/m-Â°C	8.44 Âµin/in-Â°F	
	@Temperature 0.000 - 800 Â°C	@Temperature 32.0 - 1470 Â°F	
	15.5 Âµm/m-Â°C	8.61 Âµin/in-Â°F	
	@Temperature 0.000 - 900 Â°C	@Temperature 32.0 - 1650 Â°F	
	15.8 Âµm/m-Â°C	8.78 Âµin/in-Â°F	
	@Temperature 0.000 - 1000 Â°C	@Temperature 32.0 - 1830 Â°F	
Melting Point	1255 - 1341 Â°C	2291 - 2446 Â°F	
Solidus	1255 Â°C	2291 Â°F	
Liquidus	1341 Â°C	2446 Â°F	

Component Elements Properties	Metric	English	Comments
Boron, B	1.0 %	1.0 %	
Carbon, C	1.5 %	1.5 %	
Chromium, Cr	30 %	30 %	
Cobalt, Co	48 %	48 %	As remainder
Iron, Fe	<= 3.0 %	<= 3.0 %	
Manganese, Mn	<= 1.0 %	<= 1.0 %	
Nickel, Ni	<= 3.0 %	<= 3.0 %	
Other	<= 3.0 %	<= 3.0 %	
Silicon, Si	<= 1.0 %	<= 1.0 %	
Tungsten, W	8.5 %	8.5 %	

Electrical Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Electrical Properties	Metric	English	Comments
Magnetic Permeability	@Temperature 22.0 Â°C	@Temperature 71.6 Â°F	200 Oersted

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China