

Kinetics MIM Ni as Sintered

Category : Metal , Nonferrous Metal , Nickel Alloy

Material Notes:

Most commonly used for applications requiring: Electrical conductivity Corrosion resistance. Information provided by Kinetics, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Kinetics-MIM-Ni-as-Sintered.php

Physical Properties	Metric	English	Comments
Density	8.60 g/cc	0.311 lb/in ³	Sintered Typical
	8.90 g/cc	0.322 lb/in ³	Sintered Theoretical

Electrical Properties	Metric	English	Comments
Electrical Resistivity	0.00000680 ohm-cm	0.00000680 ohm-cm	Theoretical
	0.00000930 ohm-cm	0.00000930 ohm-cm	Typical

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China