

Kingfa HF-606 Flame Retardant ABS

Category : Polymer , Thermoplastic , ABS Polymer , Acrylonitrile Butadiene Styrene (ABS), Unreinforced, Flame Retardant

Material Notes:

Features:UL 94 V-0 @ 1.6-3.0mm, 5VB @ 2.0mmHigh flowModerate UV stabilityHigh stiffnessApplications:Injection moldingMonitor cabinetCD-ROMPower switchInformation Provided by Kingfa Sci. & Tech. Co., Ltd.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Kingfa-HF-606-Flame-Retardant-ABS.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.18 g/cc	1.18 g/cc	ASTM D792
	@Temperature 23.0 Å°C	@Temperature 73.4 Å°F	
Linear Mold Shrinkage	0.0040 - 0.0060 cm/cm	0.0040 - 0.0060 in/in	ASTM D955
	@Temperature 23.0 Å°C	@Temperature 73.4 Å°F	
Melt Flow	6.0 g/10 min	6.0 g/10 min	ASTM D1238
	@Load 5.00 kg, Temperature 200 Å°C	@Load 11.0 lb, Temperature 392 Å°F	
	65 g/10 min	65 g/10 min	ASTM D1238
	@Load 10.0 kg, Temperature 220 Å°C	@Load 22.0 lb, Temperature 428 Å°F	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	104	104	ASTM D785
Tensile Strength at Break	43.0 MPa	6240 psi	50mm/min; ASTM D638
Elongation at Break	10 %	10 %	50mm/min; ASTM D638
Flexural Strength	66.0 MPa	9570 psi	2mm/min; ASTM D790
Flexural Modulus	2.40 GPa	348 ksi	2mm/min; ASTM D790
Izod Impact, Notched	1.63 J/cm	3.05 ft-lb/in	ASTM D256
	@Thickness 6.40 mm, Temperature 23.0 Å°C	@Thickness 0.252 in, Temperature 73.4 Å°F	
	1.96 J/cm	3.67 ft-lb/in	ASTM D256
	@Thickness 3.20 mm, Temperature 23.0 Å°C	@Thickness 0.126 in, Temperature 73.4 Å°F	

Thermal Properties	Metric	English	Comments
--------------------	--------	---------	----------

Thermal Properties	Metric	English	Comments
Thermal Deflection Temperature at 0.46 MPa (66 psi)	85.0 Å°C @Thickness 6.40 mm	185 Å°F @Thickness 0.252 in	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	76.0 Å°C @Thickness 6.40 mm	169 Å°F @Thickness 0.252 in	ASTM D648
Vicat Softening Point	84.0 Å°C @Load 5.00 kg	183 Å°F @Load 11.0 lb	50Å°C/min; ASTM D1525
	93.0 Å°C @Load 1.00 kg	199 Å°F @Load 2.20 lb	120Å°C/min; ASTM D1525
Flammability, UL94	V-0 @Thickness 1.60 mm	V-0 @Thickness 0.0630 in	
	V-0 @Thickness 3.00 mm	V-0 @Thickness 0.118 in	
	5VB @Thickness 2.00 mm	5VB @Thickness 0.0787 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+14 ohm-cm	1.00e+14 ohm-cm	ASTM D257
Dielectric Strength	22.0 kV/mm	559 kV/in	ASTM D149

Processing Properties	Metric	English	Comments
Processing Temperature	<= 230 Å°C	<= 446 Å°F	
Rear Barrel Temperature	160 - 180 Å°C	320 - 356 Å°F	Start Point: 170Å°C
Middle Barrel Temperature	170 - 190 Å°C	338 - 374 Å°F	Start Point: 180Å°C
Front Barrel Temperature	180 - 210 Å°C	356 - 410 Å°F	Start Point: 190Å°C
Melt Temperature	170 - 210 Å°C	338 - 410 Å°F	Start Point: 190Å°C
Mold Temperature	30.0 - 60.0 Å°C	86.0 - 140 Å°F	Start Point: 50Å°C
Drying Temperature	70.0 - 80.0 Å°C @Time 7200 - 14400 sec	158 - 176 Å°F @Time 2.00 - 4.00 hour	Pre-dry
Back Pressure	0.000 - 1.00 MPa	0.000 - 145 psi	

Descriptive Properties	Value	Comments
------------------------	-------	----------

Descriptive Properties

Value *to Moderate*

Comments

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China