

## Kingfa PA6-MG45 45% Glass & Mineral Filled PA6

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , 50% Glass Fiber Filled

### Material Notes:

Features:Low tendency to warpExcellent size stabilityLow abrasionOutstanding surfaceApplications:Injection moldingAutomobile partsInformation Provided by Kingfa Sci. & Tech. Co., Ltd.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Kingfa-PA6-MG45-45-Glass-Mineral-Filled-PA6.php](http://www.lookpolymers.com/polymer_Kingfa-PA6-MG45-45-Glass-Mineral-Filled-PA6.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.48 g/cc @Temperature 23.0 Â°C	1.48 g/cc @Temperature 73.4 Â°F	ASTM D792
Water Absorption	0.60 % @Temperature 23.0 Â°C, Time 86400 sec	0.60 % @Temperature 73.4 Â°F, Time 24.0 hour	ASTM D570
Linear Mold Shrinkage	0.0020 - 0.0030 cm/cm @Temperature 23.0 Â°C	0.0020 - 0.0030 in/in @Temperature 73.4 Â°F	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	121	121	ASTM D785
Tensile Strength at Break	130 MPa	18900 psi	10mm/min; ASTM D638
Elongation at Break	2.0 %	2.0 %	10mm/min; ASTM D638
Flexural Strength	207 MPa	30000 psi	2mm/min; ASTM D790
Flexural Modulus	0.910 GPa	132 ksi	2mm/min; ASTM D790
Izod Impact, Notched	1.85 J/cm @Thickness 3.20 mm, Temperature 23.0 Â°C	3.47 ft-lb/in @Thickness 0.126 in, Temperature 73.4 Â°F	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	219 Â°C @Thickness 6.40 mm	426 Â°F @Thickness 0.252 in	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	212 Â°C @Thickness 6.40 mm	414 Â°F @Thickness 0.252 in	ASTM D648

Thermal Properties	HB Metric	HB English	Comments
	@Thickness 1.50 mm	@Thickness 0.0591 in	
	HB	HB	
	@Thickness 3.00 mm	@Thickness 0.118 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	ASTM D257

Processing Properties	Metric	English	Comments
Processing Temperature	<= 300 Â°C	<= 572 Â°F	
Rear Barrel Temperature	225 - 245 Â°C	437 - 473 Â°F	Start Point: 230Â°C
Middle Barrel Temperature	250 - 270 Â°C	482 - 518 Â°F	Start Point: 255Â°C
Front Barrel Temperature	260 - 280 Â°C	500 - 536 Â°F	Start Point: 265Â°C
Melt Temperature	255 - 285 Â°C	491 - 545 Â°F	Start Point: 265Â°C
Mold Temperature	50.0 - 70.0 Â°C	122 - 158 Â°F	Start Point: 60Â°C
Drying Temperature	90.0 - 110 Â°C @Time 14400 - 21600 sec	194 - 230 Â°F @Time 4.00 - 6.00 hour	Pre-dry

Descriptive Properties	Value	Comments
Glass Fiber Content (%)	45	
Injection Speed	Moderate to High	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China