

Kolon ELLAS K-390A Ether Based Thermoplastic Polyurethane

Category : Polymer , Thermoplastic , Elastomer, TPE , Polyurethane, TP , Thermoplastic Polyurethane, Elastomer, Ether Grade

Material Notes:

Applications Extrusion: Cable Sheathing, high pressure tube Injection Electric Wire Industry Parts Information provided by API-Kolon.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Kolon-ELLAS-K-390A-Ether-Based-Thermoplastic-Polyurethane.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.12 g/cc	1.12 g/cc	ASTM D792

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	90	90	ASTM D2240
Tensile Strength	46.1 MPa	6680 psi	ASTM D412
Tensile Stress	8.83 MPa @Strain 100 %	1280 psi @Strain 100 %	ASTM D412
Elongation at Break	500 %	500 %	ASTM D412
Tear Strength	123 kN/m	700 pli	ASTM D624

Processing Properties	Metric	English	Comments
Nozzle Temperature	185 - 195 Å°C	365 - 383 Å°F	Injection Molding
Zone 1	155 - 175 Å°C	311 - 347 Å°F	Extrusion Molding
	160 - 175 Å°C	320 - 347 Å°F	Injection Molding
Zone 2	170 - 185 Å°C	338 - 365 Å°F	Extrusion Molding
	175 - 185 Å°C	347 - 365 Å°F	Injection Molding
Zone 3	170 - 190 Å°C	338 - 374 Å°F	Extrusion Molding
	180 - 190 Å°C	356 - 374 Å°F	Injection Molding
Zone 4	180 - 195 Å°C	356 - 383 Å°F	Extrusion Molding
Die Temperature	180 - 195 Å°C	356 - 383 Å°F	Extrusion Molding
Head Temperature	190 - 200 Å°C	374 - 392 Å°F	Extrusion Molding

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China