

## Kolon KOCETAL® K300LO Low Odor Acetal Resin

Category : Polymer , Thermoplastic , Acetal (POM)

**Material Notes:**

Low odor of formaldehyde gas. Applications: Products for low odor. Information provided by API-Kolon.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Kolon-KOCETAL-K300LO-Low-Odor-Acetal-Resin.php](http://www.lookpolymers.com/polymer_Kolon-KOCETAL-K300LO-Low-Odor-Acetal-Resin.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.41 g/cc	1.41 g/cc	ASTM D792
Linear Mold Shrinkage	0.020 cm/cm	0.020 in/in	ASTM D955
Melt Flow	8.0 - 13 g/10 min	8.0 - 13 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	80	80	ASTM D785
Tensile Strength	57.0 MPa	8270 psi	ASTM D638
Elongation at Break	40 %	40 %	ASTM D638
Flexural Strength	78.0 MPa	11300 psi	ASTM D790
Flexural Modulus	2.107 GPa	305.6 ksi	ASTM D790
Izod Impact, Notched	0.490 J/cm	0.918 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Melting Point	166 Å°C	331 Å°F	ASTM D1525
Flammability, UL94	HB	HB	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+14 ohm-cm	1.00e+14 ohm-cm	ASTM D257
Surface Resistance	1.00e+16 ohm	1.00e+16 ohm	ASTM D257

## Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China