

Kolon KOCETAL[®] K900 Standard Grade Acetal Resin

Category : Polymer , Thermoplastic , Acetal (POM) , Acetal Copolymer, Unreinforced

Material Notes:

Very low viscosity grade. Applications: Thin and large products. Information provided by API-Kolon.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Kolon-KOCETAL-K900-Standard-Grade-Acetal-Resin.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.41 g/cc	1.41 g/cc	ASTM D792
Moisture Absorption at Equilibrium	0.22 %	0.22 %	60% RH; ASTM D570
Linear Mold Shrinkage	0.020 cm/cm	0.020 in/in	ASTM D955
Melt Flow	42 g/10 min	42 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	80	80	ASTM D785
Tensile Strength	64.0 MPa	9280 psi	ASTM D638
Elongation at Break	45 %	45 %	ASTM D638
Flexural Strength	96.0 MPa	13900 psi	ASTM D790
Flexural Modulus	2.70 GPa	392 ksi	ASTM D790
Izod Impact, Notched	0.500 J/cm	0.937 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear	130 Åµm/m-Å°C	72.2 Åµin/in-Å°F	ASTM D696
Melting Point	166 Å°C	331 Å°F	ASTM D1525
Deflection Temperature at 0.46 MPa (66 psi)	158 Å°C	316 Å°F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	110 Å°C	230 Å°F	ASTM D648
Vicat Softening Point	162 Å°C	324 Å°F	ASTM D1525
Flammability, UL94	HB	HB	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+14 ohm-cm	1.00e+14 ohm-cm	ASTM D257

Electrical Properties	Metric <small>@Frequency 1.00e+6 Hz</small>	English <small>@Frequency 1.00e+6 Hz</small>	Comments
Dielectric Constant	3.7	3.7	ASTM D150
Dielectric Strength	19.0 kV/mm	483 kV/in	ASTM D149
Dissipation Factor	0.0060 <small>@Frequency 1.00e+6 Hz</small>	0.0060 <small>@Frequency 1.00e+6 Hz</small>	ASTM D150

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China