

Kolon KOCETAL[®] SO301 Wear Modified Acetal Resin

Category : Polymer , Thermoplastic , Acetal (POM) , Acetal Copolymer, Silicone Filled

Material Notes:

Silicone Oil added, improved wear property. Information provided by API-Kolon.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Kolon-KOCETAL-SO301-Wear-Modified-Acetal-Resin.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.40 g/cc	1.40 g/cc	ASTM D792
Linear Mold Shrinkage	0.020 cm/cm	0.020 in/in	ASTM D955
Melt Flow	9.0 - 12 g/10 min	9.0 - 12 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	80	80	ASTM D785
Tensile Strength	44.0 MPa	6380 psi	ASTM D638
Elongation at Break	50 %	50 %	ASTM D638
Flexural Strength	74.0 MPa	10700 psi	ASTM D790
Flexural Modulus	2.156 GPa	312.7 ksi	ASTM D790
Izod Impact, Notched	0.440 J/cm	0.824 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Melting Point	166 Å°C	331 Å°F	ASTM D1525
Flammability, UL94	HB	HB	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+14 ohm-cm	1.00e+14 ohm-cm	ASTM D257
Surface Resistance	1.00e+16 ohm	1.00e+16 ohm	ASTM D257

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China