

## Kolon KOPA<sup>®</sup> KN163HI High Impact Nylon 6

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , Impact Grade

### Material Notes:

KOPA<sup>®</sup> is a thermoplastic resin with excellent mechanical, thermal and electrical properties and is widely used in automobile and industrial parts. Good mechanical properties, outstanding self-lubrication and abrasion resistance, excellent chemical resistance, wide usage temperature, good impact absorbing characteristics. Information provided by US distributor, API-Kolon.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Kolon-KOPA-KN163HI-High-Impact-Nylon-6.php](http://www.lookpolymers.com/polymer_Kolon-KOPA-KN163HI-High-Impact-Nylon-6.php)

Physical Properties	Metric	English	Comments
Density	1.05 g/cc	0.0379 lb/in <sup>3</sup>	DIN 53479; ASTM D792
Water Absorption	0.30 %	0.30 %	DIN 53475; ASTM D570
Linear Mold Shrinkage	0.012 - 0.014 cm/cm	0.012 - 0.014 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	110	110	DIN 53505; ASTM D785
Tensile Strength, Ultimate	49.0 MPa	7110 psi	DIN 53455; ASTM D638
Elongation at Break	90 %	90 %	DIN 53455; ASTM D638
Flexural Yield Strength	78.5 MPa	11400 psi	DIN 53455; ASTM D790
Flexural Modulus	2.06 GPa	299 ksi	DIN 53452; ASTM D790
Izod Impact, Notched	8.83 J/cm	16.5 ft-lb/in	DIN 53453; ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear	90.0 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$	50.0 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$	DIN 53752; ASTM D696
	@Temperature 20.0 $\text{Å}^\circ\text{C}$	@Temperature 68.0 $\text{Å}^\circ\text{F}$	
Melting Point	220 $\text{Å}^\circ\text{C}$	428 $\text{Å}^\circ\text{F}$	DIN 53736; ASTM D789
Deflection Temperature at 0.46 MPa (66 psi)	130 $\text{Å}^\circ\text{C}$	266 $\text{Å}^\circ\text{F}$	DIN 53461; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	65.0 $\text{Å}^\circ\text{C}$	149 $\text{Å}^\circ\text{F}$	DIN 53461; ASTM D648
Flammability, UL94	HB	HB	

Electrical Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Electrical Properties	<sup>3.2</sup> Metric	<sup>3.2</sup> English	Comments
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	/DIN 53483
Dielectric Strength	20.0 kV/mm	508 kV/in	ASTM D149/DIN 53481
Arc Resistance	120 sec	120 sec	ASTM D495

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China