

Kolon KOPA[®] KN333HI2 High Impact Nylon 66

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, Impact Grade

Material Notes:

KOPA[®] is a thermoplastic resin with excellent mechanical, thermal and electrical properties and is widely used in the automobile, electrical and industrial parts. High tensile strength, outstanding self lubrication and abrasion resistance, excellent chemical & weather resistance, high usage temperature. Information provided by US distributor, API-Kolon.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Kolon-KOPA-KN333HI2-High-Impact-Nylon-66.php

Physical Properties	Metric	English	Comments
Density	1.12 g/cc	0.0405 lb/in ³	DIN 53479; ASTM D792
Water Absorption	1.0 %	1.0 %	DIN 53475; ASTM D570
Linear Mold Shrinkage	0.012 - 0.014 cm/cm	0.012 - 0.014 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	110	110	DIN 53505; ASTM D785
Tensile Strength, Ultimate	63.7 MPa	9250 psi	DIN 53455; ASTM D638
Elongation at Break	70 %	70 %	DIN 53455; ASTM D638
Flexural Yield Strength	88.3 MPa	12800 psi	DIN 53455; ASTM D790
Flexural Modulus	1.86 GPa	270 ksi	DIN 53452; ASTM D790
Izod Impact, Notched	2.45 J/cm	4.59 ft-lb/in	DIN 53453; ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear	60.0 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$	33.3 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$	DIN 53752; ASTM D696
	@Temperature 20.0 $\text{Å}^\circ\text{C}$	@Temperature 68.0 $\text{Å}^\circ\text{F}$	
Melting Point	255 $\text{Å}^\circ\text{C}$	491 $\text{Å}^\circ\text{F}$	DIN 53736; ASTM D789
Deflection Temperature at 0.46 MPa (66 psi)	220 $\text{Å}^\circ\text{C}$	428 $\text{Å}^\circ\text{F}$	DIN 53461; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	75.0 $\text{Å}^\circ\text{C}$	167 $\text{Å}^\circ\text{F}$	DIN 53461; ASTM D648
Flammability, UL94	HB	HB	

Electrical Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Electrical Properties	^{3.1} Metric	^{3.1} English	Comments <small>/DIN 53483</small>
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Dielectric Strength	20.0 kV/mm	508 kV/in	ASTM D149/DIN 53481
Arc Resistance	125 sec	125 sec	ASTM D495

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China