

Kolon Kocetal® EC701 Modified Grade Acetal Copolymer (discontinued **)

Category : Polymer , Thermoplastic , Acetal (POM) , Acetal Copolymer, Unreinforced

Material Notes:

Thermal properties: Kocetal has excellent heat stability; heat degradation is little under long term and high temperature application, compared to other POM. Maximum applicable temperature of products of Kocetal are short term: 140-150C and long term: 100-120C. **Mechanical Properties:** Kocetal is an engineering plastic that has excellent strength, stiffness and wear endurance. Also, it offers an excellent balance of several properties. For example, mechanical properties are stable in the practical temperature zone (-50C to 80C), compared to Nylon and PBT resins. Although it has slightly lower initial strength, compared to homopolymer, the long term properties of "elongation at break and impact strength" are superior. **Electrical Properties:** Kocetal has excellent electrical properties. Its electrical properties, volume resistivity, dielectric constant, dissipation factor and dielectric strength change little with temperature. It also has a feature of good anti-pollution properties on electrical contact. Kocetal has such a permanent anti-static grade that can be applied to the specifics. **Chemical Properties:** Kocetal has excellent chemical resistance to organic chemicals, oils, fats and detergents. It is also strongly resistant to inorganic chemicals except strong acids. Information provided by US distributor, API-Kolon.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Kolon-Kocetal-EC701-Modified-Grade-Acetal-Copolymer-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	1.40 g/cc	0.0506 lb/in ³	ASTM D790
Water Absorption	0.22 %	0.22 %	ASTM D570
Linear Mold Shrinkage	0.020 cm/cm	0.020 in/in	ASTM D955
Melt Flow	27 g/10 min	27 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	80	80	ASTM D785
Tensile Strength, Ultimate	58.8 MPa	8530 psi	ASTM D638
Elongation at Break	50 %	50 %	ASTM D638
Flexural Yield Strength	79.4 MPa	11500 psi	ASTM D790
Flexural Modulus	2.55 GPa	370 ksi	ASTM D790
Izod Impact, Notched	0.588 J/cm	1.10 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear	110 - 130 µm/m-°C	61.1 - 72.2 µin/in-°F	ASTM D696
	@Temperature 20.0 °C	@Temperature 68.0 °F	
Melting Point	166 °C	331 °F	ASTM D1525

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	120 °C	248 °F	Long Term
	140 - 150 °C	284 - 302 °F	Short Term
Deflection Temperature at 0.46 MPa (66 psi)	160 °C	320 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	110 °C	230 °F	ASTM D648
Flammability, UL94	HB	HB	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+10 ohm-cm	1.00e+10 ohm-cm	ASTM D257
Surface Resistance	1.00e+11 ohm	1.00e+11 ohm	ASTM D257

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China