

Kolon Kopa® KN173HI Nylon 6 Resin

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , Unreinforced

Material Notes:

KOPA is widely used in the automobile and industrial parts. General KOPA N-6 Features: Good mechanical properties, Extreme toughness, Outstanding self-lubrication and abrasion resistance, Excellent chemical resistance, Wide usage temperature, Good impact absorbing characteristics. Information provided by US distributor, API-Kolon.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Kolon-Kopa-KN173HI-Nylon-6-Resin.php

Physical Properties	Metric	English	Comments
Density	1.12 g/cc	0.0405 lb/in ³	DIN 53479; ASTM D792
Water Absorption	1.5 %	1.5 %	DIN 53475; ASTM D570
Linear Mold Shrinkage	0.013 - 0.016 cm/cm	0.013 - 0.016 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	115	115	DIN 53505; ASTM D785
Tensile Strength, Ultimate	64.0 MPa	9280 psi	DIN 53455; ASTM D638
Elongation at Break	200 %	200 %	DIN 53455; ASTM D638
Flexural Yield Strength	98.0 MPa	14200 psi	DIN 53452; ASTM D790
Flexural Modulus	2.00 GPa	290 ksi	DIN 53452; ASTM D790
Izod Impact, Notched	0.980 J/cm	1.84 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear	100 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$	55.6 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$	DIN 53752; ASTM D696
	@Temperature 20.0 $\text{Å}^\circ\text{C}$	@Temperature 68.0 $\text{Å}^\circ\text{F}$	
Melting Point	220 $\text{Å}^\circ\text{C}$	428 $\text{Å}^\circ\text{F}$	DIN 53736; ASTM D789
Deflection Temperature at 0.46 MPa (66 psi)	170 $\text{Å}^\circ\text{C}$	338 $\text{Å}^\circ\text{F}$	DIN 53461; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	62.0 $\text{Å}^\circ\text{C}$	144 $\text{Å}^\circ\text{F}$	DIN 53461; ASTM D648
Flammability, UL94	HB	HB	

Electrical Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Electrical Properties	^{3.2} Metric	^{3.2} English	Comments
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	/DIN 53483
Dielectric Strength	20.0 kV/mm	508 kV/in	ASTM D149/DIN 53481
Arc Resistance	125 sec	125 sec	ASTM D495

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China