

Kolon NOPLA[®] KE831 PEN-PET Copolyester

Category : Polymer , Thermoplastic , Polyester, TP , Polyethylene Terephthalate (PET) , PEN-PET

Material Notes:

NOPLA[®] is an advanced PEN-PET copolyester which can be used for bottle, sheet & injection molding applications UV protection & prolonged outdoor durability, enhanced gas barrier, outstanding impact strength, excellent chemical and hydrolytic resistance, higher thermal performance, excellent clarity, recyclable & non-toxic, low flammability Information provided by US distributor, API-Kolon.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Kolon-NOPLA-KE831-PEN-PET-Copolyester.php

Physical Properties	Metric	English	Comments
Density	1.33 g/cc	0.0480 lb/in ³	DIN 53479; ASTM D792
Water Absorption	0.070 %	0.070 %	DIN 53475; ASTM D570
Linear Mold Shrinkage	0.0040 - 0.0060 cm/cm	0.0040 - 0.0060 in/in	ASTM D955
Melt Flow	15 g/10 min @Temperature 275 Â°C	15 g/10 min @Temperature 527 Â°F	DSC

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	88	88	DIN 53505; ASTM D785
Tensile Strength, Ultimate	60.0 MPa	8700 psi	DIN 53455; ASTM D638
Elongation at Break	460 %	460 %	DIN 53455; ASTM D638
Flexural Yield Strength	92.2 MPa	13400 psi	DIN 53455; ASTM D790
Flexural Modulus	2.85 GPa	414 ksi	DIN 53452; ASTM D790
Izod Impact, Notched	0.539 J/cm	1.01 ft-lb/in	DIN 53453; ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear	60 Âµm/m-Â°C @Temperature 20.0 Â°C	33 Âµin/in-Â°F @Temperature 68.0 Â°F	DIN 53752; ASTM D696
Melting Point	234 Â°C	453 Â°F	DIN 53736; ASTM D789
Deflection Temperature at 0.46 MPa (66 psi)	77.0 Â°C	171 Â°F	ASTM D648
Glass Transition Temp, Tg	84.0 Â°C	183 Â°F	DSC
Flammability, UL94	V-2	V-2	

Optical Properties	Metric	English	Comments
Haze	1.0 %	1.0 %	ASTM D1003

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China