

## Kolon NOPLA<sup>®</sup> KE931 PEN-PET Copolyester

Category : Polymer , Thermoplastic , Polyester, TP , Polyethylene Terephthalate (PET) , PEN-PET

### Material Notes:

NOPLA<sup>®</sup> is an advanced PEN-PET copolyester which can be used for bottle, sheet & injection molding applications UV protection & prolonged outdoor durability, enhanced gas barrier, outstanding impact strength, excellent chemical and hydrolytic resistance, higher thermal performance, excellent clarity, recyclable & non-toxic, low flammability Information provided by US distributor, API-Kolon.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Kolon-NOPLA-KE931-PEN-PET-Copolyester.php](http://www.lookpolymers.com/polymer_Kolon-NOPLA-KE931-PEN-PET-Copolyester.php)

Physical Properties	Metric	English	Comments
Density	1.33 g/cc	0.0480 lb/in <sup>3</sup>	DIN 53479; ASTM D792
Water Absorption	0.060 %	0.060 %	DIN 53475; ASTM D570
Linear Mold Shrinkage	0.0040 - 0.0060 cm/cm	0.0040 - 0.0060 in/in	ASTM D955
Melt Flow	12 g/10 min @Temperature 275 Â°C	12 g/10 min @Temperature 527 Â°F	DSC

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	110	110	DIN 53505; ASTM D785
Tensile Strength, Ultimate	81.4 MPa	11800 psi	DIN 53455; ASTM D638
Elongation at Break	50 %	50 %	DIN 53455; ASTM D638
Flexural Yield Strength	91.2 MPa	13200 psi	DIN 53455; ASTM D790
Flexural Modulus	2.48 GPa	360 ksi	DIN 53452; ASTM D790
Izod Impact, Notched	0.441 J/cm	0.827 ft-lb/in	DIN 53453; ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear	60 Âµm/m-Â°C @Temperature 20.0 Â°C	33 Âµin/in-Â°F @Temperature 68.0 Â°F	DIN 53752; ASTM D696
Melting Point	255 Â°C	491 Â°F	DIN 53736; ASTM D789
Deflection Temperature at 0.46 MPa (66 psi)	115 Â°C	239 Â°F	ASTM D648
Glass Transition Temp, Tg	121 Â°C	250 Â°F	DSC
Flammability, UL94	V-2	V-2	

Optical Properties	Metric	English	Comments
Haze	1.5 %	1.5 %	ASTM D1003

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China