

Kraton® D1117 P (SIS) Linear Triblock Copolymer

Category : Polymer , Thermoplastic , Elastomer, TPE

Material Notes:

Description: Kraton D1117 P is a clear, linear triblock copolymer based on styrene and isoprene with a polystyrene content of 17%. It is supplied from North America in the physical form identified: Kraton D1117 PT - supplied as a dusted dense pellet
Region: South America, Europe, Asia Pacific, North America, and Japan
Uses: Kraton D1117 P is used as an ingredient in formulating adhesives, sealants and coatings. It may also find use as a modifier of bitumen or thermoplastics and in compound formulations.
Applications: Adhesives, Sealant and Coatings; Compounding and Personal Hygiene; Impact Modification; Footwear; and Bitumen Modification
 Information provided by Kraton®

Order this product through the following link:

http://www.lookpolymers.com/polymer_Kraton-D1117-P-SIS-Linear-Triblock-Copolymer.php

Physical Properties	Metric	English	Comments
Specific Gravity	0.920 g/cc	0.920 g/cc	ASTM D4025
Volatiles	<= 0.50 %	<= 0.50 %	KM 04
Viscosity	350 - 590 cP	350 - 590 cP	25% Toluene Solution at 25Å°C; BAM 922
Melt Flow	29 g/10 min @Load 5.00 kg, Temperature 200 Å°C	29 g/10 min @Load 11.0 lb, Temperature 392 Å°F	
Ash	0.30 - 0.40 %	0.30 - 0.40 %	Talc; BAM 908

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	33 @Time 10.0 sec	33 @Time 0.00278 hour	Typical values on polymer compression molded at 300Å°F; ASTM D2240
Tensile Strength	8.27 MPa	1200 psi	Typical properties on film cast from toluene solution; ASTM D412
Elongation at Break	1300 %	1300 %	Typical properties of film cast from toluene solution; ASTM D412
300% Modulus	0.000414 GPa	0.0600 ksi	Typical properties of film cast form toluene solution; ASTM D412

Chemical Properties	Metric	English	Comments
Diblock Content	33 %	33 %	

Descriptive Properties	Value	Comments
Content	Antioxidant	0.08-0.3%, KM 08

Descriptive Properties	Value	Comments
	Styrene	KM 03
	Total Extractables	<1.0%, KM 05
Styrene/Rubber Ratio	17/83	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China