

## Kraton® D1118 K (SBS) Diblock Copolymer

Category : Polymer , Thermoplastic , Styrene-Butadiene , Styrene/Butadiene/Styrene (SBS)

### Material Notes:

Description: Kraton D1118 K is a clear, diblock copolymer based on styrene and butadiene with a polystyrene content of 33%. It is supplied from North America in the physical form identified: Kraton D1118 KT - supplied as a dusted porous pellet; Kraton D1118 KTM - supplied as a dusted powder. Region: Asia Pacific, Europe, Japan, North America, and South America. Uses: Kraton D1118 K is used as a modifier of bitumen or thermoplastics and in compound formulations. It may also find use as an ingredient in formulating adhesives, sealants and coatings. Applications: Adhesives, Sealant and Coatings; Bitumen Modification; Compounding and Personal Hygiene; Footwear; Impact Modification; Medical; Packaging and Polymod; Personal Care; and Roads and Roofing. Note 1) The final dusting level is a combination of the talc from the original D1118 KT plus PGA-SD Alumina added during the milling process. Information provided by Kraton®

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Kraton-D1118-K-SBS-Diblock-Copolymer.php](http://www.lookpolymers.com/polymer_Kraton-D1118-K-SBS-Diblock-Copolymer.php)

Physical Properties	Metric	English	Comments
Specific Gravity	0.940 g/cc	0.940 g/cc	ASTM D4025
Volatiles	<= 1.0 %	<= 1.0 %	KM 04
Viscosity	470 - 790 cP	470 - 790 cP	25% Toluene Solution at 25°C; BAM 922
Melt Flow	10 g/10 min @Load 5.00 kg, Temperature 200 °C	10 g/10 min @Load 11.0 lb, Temperature 392 °F	
Ash	0.40 - 0.65 %	0.40 - 0.65 %	KT, Talc; BAM 908
	4.0 - 6.0 %	4.0 - 6.0 %	KIM, See Note 1); BAM 908

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	74 @Time 10.0 sec	74 @Time 0.00278 hour	Typical values on polymer compression molded at 350°F; ASTM D2240
Tensile Strength	1.72 MPa	249 psi	Typical properties of film cast from toluene solution; ASTM D412
Elongation at Break	600 %	600 %	Measured on films cast from a solution in toluene; ASTM D412
300% Modulus	0.00120 GPa	0.174 ksi	Measured on films cast from a solution in toluene; ASTM D412

Chemical Properties	Metric	English	Comments
Diblock Content	78 %	78 %	

Descriptive Properties	Value	Comments
Content	Non-staining phenolic antioxidant	0.15-0.4%, KM 08
	Polystyrene	31-35%, KM 03
	Total Extractables	<1.0%, KM 05
Styrene/Rubber Ratio	33/67	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China