## Kraton® G1650 E (SEBS) Linear Triblock Copolymer

Category : Polymer , Thermoplastic , Elastomer, TPE

## Material Notes:

Description: Kraton G1650 E is a clear linear triblock copolymer based on styrene and ethylene/butylene, S-E/B-S, with bound styrene of 29.2% mass. It is supplied from Europe in the physical forms identified: Kraton G1650 EU - supplied as undusted fluffy crumbKraton G1650 ES - supplied as fluffy crumb dusted with amorphous silicaRegion: Asia Pacific, Europe, Japan, North America, and South AmericaUses: Kraton G1650 EU - supplied as undusted fluffy crumb Kraton G1650 ES - supplied as fluffy crumb dusted with amorphous silicaApplications: Adhesives, Sealant and Coatings; Compounding and Personal Hygiene; Impact Modification; Medical; Packaging and Polymod; Personal Care; Bitumen Modification; and Roads and RoofingInformation provided by Kraton®

## Order this product through the following link:

http://www.lookpolymers.com/polymer\_Kraton-G1650-E-SEBS-Linear-Triblock-Copolymer.php

| Physical Properties | Metric         | English        | Comments                               |
|---------------------|----------------|----------------|--|
| Specific Gravity    | 0.910 g/cc     | 0.910 g/cc     | ISO 2781                               |
| Volatiles           | <= 0.50 %      | <= 0.50 %      | KM 04                                  |
| Viscosity           | 1000 - 1900 cP | 1000 - 1900 cP | 20% Toluene Solution at 25°C; KM<br>06 |
| Ash                 | 0.40 - 0.60 %  | 0.40 - 0.60 %  | ES; ISO 247                            |

| Mechanical Properties | Metric      | English   | Comments  |
|-----------------------|-------------|-----------|---|
| Tensile Strength      | 35.0 MPa    | 5080 psi  | Measured on films cast from solution in toluene; ISO 37 |
| Elongation at Break   | 500 %       | 500 %     | Measured on films cast from solution in toluene; ISO 37 |
| 300% Modulus          | 0.00560 GPa | 0.812 ksi | Measured on films cast from solution in toluene; ISO 27 |

| Descriptive Properties | Value              | Comments          |
|------------------------|--------------------|-------------------|
| Content                | Antioxidant        | >0.03%, KM 08     |
|                        | Polystyrene        | 27.7-30.7%, KM 03 |
|                        | Total Extractables | <1.0%, KM 05      |

## Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com Email : sales@lookpolymers.com Tel : +86 021-51131842 Mobile : +86 13061808058



Skype : lookpolymers Address : United North Road 215,Fengxian District, Shanghai City,China