

Kraton® G1651 + PC blend (5/95)

Category : Polymer , Thermoplastic , Elastomer, TPE , Polycarbonate (PC)

Material Notes:

Blending KRATON D and G polymers with PC significantly improves the toughness at both room and low temperatures. KRATON polymers are block segments of styrene and rubber monomers (A-B, A-B-A, or [A-B]n). The KRATON G series are second generation block polymers in which the rubber monomer is a saturated olefin polymer, either ethylene/butylene or ethylene/propylene. Kraton G polymer grades manufactured in France are labeled with an "E" for standard grades and "ES" for grades dusted with silica, for distribution in Europe, Africa and Asia Pacific. Information provided by the manufacturer, Kraton® Polymers.

Order this product through the following link: http://www.lookpolymers.com/polymer_Kraton-G1651-PC-blend-595.php

Mechanical Properties	Metric	English	Comments
Flexural Modulus	2.30 GPa	334 ksi	
Izod Impact, Notched	2.14 J/cm	4.01 ft-lb/in	notch
	@Thickness 3.17 mm, Temperature -40.0 °C	@Thickness 0.125 in, Temperature -40.0 °F	
	8.49 J/cm	15.9 ft-lb/in	
	@Thickness 3.17 mm, Temperature 23.0 °C	@Thickness 0.125 in, Temperature 73.4 °F	notch

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com Email : sales@lookpolymers.com Tel : +86 021-51131842 Mobile : +86 13061808058 Skype : lookpolymers Address : United North Road 215,Fengxian District, Shanghai City,China