

Kraton® G1657 + PA-6,6 blend (8/12/80)

Category : Polymer , Thermoplastic , Elastomer, TPE , Nylon

Material Notes:

Blending KRATON D and G polymers with PA significantly improves the toughness at both room and low temperatures. KRATON polymers are block segments of styrene and rubber monomers (A-B, A-B-A, or [A-B]_n). The KRATON G series are second generation block polymers in which the rubber monomer is a saturated olefin polymer, either ethylene/butylene or ethylene/propylene. KRATON FG polymers are functionalized versions of the G series. Available in the U.S. only. Information provided by the manufacturer, Kraton® Polymers.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Kraton-G1657-PA-66-blend-81280.php

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	45.0 MPa	6530 psi	
Elongation at Break	24 %	24 %	
Flexural Modulus	1.86 GPa	270 ksi	
Izod Impact, Notched	2.72 J/cm @Temperature -29.0 °C	5.10 ft-lb/in @Temperature -20.2 °F	3.2 mm (0.125 in) notch
	10.62 J/cm @Temperature 23.0 °C	19.90 ft-lb/in @Temperature 73.4 °F	3.2 mm (0.125 in) notch

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China