

Kuraray Genestar[®],ç GN2332 Nylon, 33% Glass Filled

Category : Polymer , Thermoplastic , Nylon

Material Notes:

High Flow V-0 Grade. Improves flow-ability in thin-walled parts. Used for components requiring high-flowability, such as 0.3 mm pitch connectors.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Kuraray-Genestar-GN2332-Nylon-33-Glass-Filled.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.62 g/cc	1.62 g/cc	
Water Absorption	1.0 %	1.0 %	
Linear Mold Shrinkage, Flow	0.0010 cm/cm	0.0010 in/in	
Linear Mold Shrinkage, Transverse	0.0060 cm/cm	0.0060 in/in	
Melt Flow	60 g/10 min @Load 2.16 kg, Temperature 320 Â°C	60 g/10 min @Load 4.76 lb, Temperature 608 Â°F	ASTM D1238
Spiral Flow	8.50 cm @Load 750 kg, Temperature 320 Â°C	3.35 in @Load 1650 lb, Temperature 608 Â°F	0.5mm diameter

Mechanical Properties	Metric	English	Comments
Tensile Strength	36.0 MPa	5220 psi	Weld; ASTM D638
	165 MPa	23900 psi	ASTM D638
Elongation at Yield	0.30 %	0.30 %	Weld; ASTM D638
	3.8 %	3.8 %	ASTM D638
Flexural Strength	215 MPa	31200 psi	ASTM D790
Flexural Modulus	11.0 GPa	1600 ksi	ASTM D790
Izod Impact, Notched	1.10 J/cm	2.06 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Melting Point	306 Â°C	583 Â°F	
Deflection Temperature at 1.8 MPa (264 psi)	285 Â°C	545 Â°F	ASTM D648
Glass Transition Temp, Tg			

Thermal Properties	125 Å°C Metric	257 Å°F English	Comments
Flammability, UL94	V-0	V-0	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+16 ohm-cm	1.00e+16 ohm-cm	ASTM D257
Dielectric Constant	3.4 @Frequency 1.00e+10 Hz	3.4 @Frequency 1.00e+10 Hz	ASTM D150
Dielectric Strength	30.0 kV/mm	762 kV/in	ASTM D149
Dielectric Loss Index	0.010 @Frequency 1.00e+10 Hz	0.010 @Frequency 1.00e+10 Hz	ASTM D150
Comparative Tracking Index	400 - 600 V	400 - 600 V	ASTM UL746A

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China