

Kuraray HYBRARÂ® HD3 Thermoplastic Rubber-HDPE Blend

Category : Polymer , Thermoplastic , Elastomer, TPE , Thermoplastic Elastomer, Melt-Processible Rubber , Polyethylene (PE) , HDPE

Material Notes:

Description: HYBRARÂ® is another in the series of new high performance thermoplastic rubbers developed by KURARAY using their unique isoprene technology. HYBRARÂ® is a special thermoplastic rubber which exhibits high vibration damping properties at room temperatures. Both hydrogenated and non-hydrogenated grades of HYBRARÂ® are available. In addition to the superior vibration damping properties, hydrogenated grades also exhibit excellent miscibility with polypropylene, and may be used to produce blends with excellent transparency, flexibility and mechanical properties. Blends of HYBRARÂ® and other polymers exhibit excellent vibration damping properties. Mixing Conditions: Brabender Plasticorder @ 200Â°C Molding Conditions: Press Molding @ 210Â°C Formulation (parts by weight): High Density Polyethylene - 90, HYBRARÂ® 5127 - 10 Information provided by The Kuraray Group.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Kuraray-HYBRAR-HD3-Thermoplastic-Rubber-HDPE-Blend.php

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	58	58	
Tensile Strength, Ultimate	25.0 MPa	3630 psi	
Tensile Strength, Yield	47.0 MPa	6820 psi	
Elongation at Break	1655 %	1655 %	
Tensile Modulus	0.853 GPa	124 ksi	

Descriptive Properties	Value	Comments
Loss Factor	0.077	at 40Â°C, measured w/ Rheovibron @ 110 Hz
Tan Delta	0.036	measured by resonance method with a cantilever beam
	0.07	at 0Â°C, measured w/ Rheovibron @ 11 Hz
	0.072	at 25Â°C, measured w/ Rheovibron @ 110 Hz

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China