

Kuraray HYBRARÂ® PH7 Polypropylene Blend

Category : Polymer , Thermoplastic , Elastomer, TPE , Thermoplastic Elastomer, Melt-Processible Rubber , Polypropylene (PP)

Material Notes:

Description: HYBRARÂ® is another in the series of new high performance thermoplastic rubbers developed by KURARAY using their unique isoprene technology. HYBRARÂ® is a special thermoplastic rubber which exhibits high vibration damping properties at room temperatures. Both hydrogenated and non-hydrogenated grades of HYBRARÂ® are available. In addition to the superior vibration damping properties, hydrogenated grades also exhibit excellent miscibility with polypropylene, and may be used to produce blends with excellent transparency, flexibility and mechanical properties. A flexible and transparent compound may be obtained by combining a hydrogenated HYBRARÂ® resin with polypropylene. A homopolymer or random copolymer polypropylene can be used for this application. These compounds have high tensile strength and excellent impact strength. They may be used for film, sheet or profile extrusion applications and make an excellent alternative to flexible PVC. Mixing Condition: Twin screw extruder @ 210Â°C Molding Condition: Press molding @ 210Â°C Formulation (parts by weight): Polypropylene (Homopolymer) - 70, HYBRARÂ® 7311 - 30 Information provided by The Kuraray Group.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Kuraray-HYBRAR-PH7-Polypropylene-Blend.php

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	96	96	
Tensile Strength, Ultimate	30.0 MPa	4350 psi	
Tensile Modulus	0.140 GPa	20.3 ksi	
Izod Impact, Notched	3.18 J/cm	5.96 ft-lb/in	
	@Temperature -20.0 Â°C	@Temperature -4.00 Â°F	

Optical Properties	Metric	English	Comments
Haze	33 %	33 %	
	@Thickness 1.00 mm	@Thickness 0.0394 in	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China