

Kuraray SEPTON® S4077 Thermoplastic Rubber

Category: Polymer, Thermoplastic, Elastomer, TPE, Thermoplastic Elastomer, Melt-Processible Rubber

Material Notes:

SEPTON® is a series of high performance thermoplastic rubbers developed by Kuraray Co. Ltd. using its isoprene technology. SEPTON® resins are hydrogenated styrenic block copolymers, which exhibit rubber-like properties over a wide range of temperatures. SEPTON®'s characteristics include:Excellent Mechanical PropertiesGood WeatherabilityExcellent Low Temperature PropertiesExcellent Electrical PropertiesSuperior Heat ResistanceExcellent Chemical ResistanceLow ToxicitySEPTON® grades are available with a range of Shore A hardness of 35-95 and tensile strengths of 290-5600 psi. SEPTON® resins are highly extendible with fillers, resins and oils, which allows formulation of a variety of hardness for adhesives, sealants and various compounds. As an additive, SEPTON® resins can be used to improve toughness of a variety of plastics. Several SEPTON® grades have U.S. FDA and USP Class VI approval.SEPTON® has a versatile series of grades which can be used in numerous processing techniques such as blow molding, injection molding, extrusion, hot melt and solution coatings. SEPTON® resins are thermoplastics therefore, the scrap is recyclable without significant loss of properties.Information provided by The Kuraray Group.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Kuraray-SEPTON-S4077-Thermoplastic-Rubber.php

Physical Properties	Metric	English	Comments
Specific Gravity	0.910 g/cc	0.910 g/cc	ISO 1183
Viscosity	300 cP	300 cP	5% wt Toluene Solution
	@Temperature 30.0 °C	@Temperature 86.0 °F	

Chemical Properties	Metric	English	Comments
Styrene Content	30 %	30 %	

Descriptive Properties	Value	Comments
Physical Form	Crumb	

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China