

## Kureha KF Polymer 1300 PVDF Homopolymer

Category : Polymer , Thermoplastic , Fluoropolymer , PVDF , Polyvinylidene fluoride (PVDF), Molded/Extruded

### Material Notes:

KF Polymer is a fire-resistant engineering plastic which maintains the excellent performance of a fluoropolymer. It shows well-balanced molding processability similar to general-purpose resins. KF polymer is being used in applications where heat resistance, anticorrosion, and weather-resistance are important. Typical Applications: Chemical valves, Pump part, & Fittings Binder for lithium ion batteries Hollow fiber for filtration of city water and sewage Film & Sheet Information provided by Kureha.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Kureha-KF-Polymer-1300-PVDF-Homopolymer.php](http://www.lookpolymers.com/polymer_Kureha-KF-Polymer-1300-PVDF-Homopolymer.php)

Physical Properties	Metric	English	Comments
Density	1.77 - 1.79 g/cc	0.0639 - 0.0647 lb/in <sup>3</sup>	ASTM D792
Viscosity	5000 cP @Shear Rate 50.0 1/s, Temperature 240 Â°C	5000 cP @Shear Rate 50.0 1/s, Temperature 464 Â°F	Melt; ASTM D3835
Viscosity Test	1.3 cm <sup>3</sup> /g @Temperature 30.0 Â°C	1.3 cm <sup>3</sup> /g @Temperature 86.0 Â°F	Inherent Viscosity in DMF Solution
Melt Flow	0.60 - 0.90 g/10 min @Load 5.00 kg, Temperature 230 Â°C	0.60 - 0.90 g/10 min @Load 11.0 lb, Temperature 446 Â°F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	67.0 MPa	9720 psi	ISO 527-2
Elongation at Break	25 %	25 %	ISO 527-2
Tensile Modulus	2.58 GPa	374 ksi	ISO 527-2

Thermal Properties	Metric	English	Comments
Melting Point	173 Â°C	343 Â°F	ASTM D3418
Deflection Temperature at 1.8 MPa (264 psi)	72.0 Â°C	162 Â°F	ISO 75-2
Flammability, UL94	V-0 @Thickness 1.47 mm	V-0 @Thickness 0.0579 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1e+15 - 1e+16 ohm-cm	1e+15 - 1e+16 ohm-cm	ASTM D257

Electrical Properties

Metric

English

Comments

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China