

## Kureha KF Polymer 1700 High Viscosity PVDF Homopolymer

Category : Polymer , Thermoplastic , Fluoropolymer , PVDF , Polyvinylidene fluoride (PVDF), Molded/Extruded

**Material Notes:**

KF Polymer is a fire-resistant engineering plastic which maintains the excellent performance of a fluoropolymer. It shows well-balanced molding processability similar to general-purpose resins. KF polymer is being used in applications where heat resistance, anticorrosion, and weather-resistance are important. Typical Applications: Chemical valves, Pump part, & Fittings Binder for lithium ion batteries Hollow fiber for filtration of city water and sewage Film & Sheet Information provided by Kureha.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Kureha-KF-Polymer-1700-High-Viscosity-PVDF-Homopolymer.php](http://www.lookpolymers.com/polymer_Kureha-KF-Polymer-1700-High-Viscosity-PVDF-Homopolymer.php)

Physical Properties	Metric	English	Comments
Density	1.77 - 1.79 g/cc	0.0639 - 0.0647 lb/in <sup>3</sup>	ASTM D792
Viscosity	9100 cP @Shear Rate 50.0 1/s, Temperature 260 Â°C	9100 cP @Shear Rate 50.0 1/s, Temperature 500 Â°F	Melt; ASTM D3835
Viscosity Test	170 cm <sup>3</sup> /g @Temperature 30.0 Â°C	170 cm <sup>3</sup> /g @Temperature 86.0 Â°F	Inherent Viscosity in DMF Solution
Melt Flow	1.7 g/10 min @Load 21.6 kg, Temperature 230 Â°C	1.7 g/10 min @Load 47.6 lb, Temperature 446 Â°F	ASTM D1238

Thermal Properties	Metric	English	Comments
Melting Point	173 Â°C	343 Â°F	ASTM D3418
Flammability, UL94	V-0	V-0	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1e+14 - 1e+15 ohm-cm	1e+14 - 1e+15 ohm-cm	ASTM D257

## Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China