

LATI Lasulf G/15 PSU, 15% Glass Fiber Reinforced

Category : Polymer , Thermoplastic , Polysulfone (PSU) , Polysulfone, 20% Glass Fiber Reinforced

Material Notes:

Polysulfone (PSU) based compound. Glass fibers. Low smoke density and low toxicity index. Very high dimensional stabilityAvailability: Africa & Middle East; Asia Pacific; Europe; Latin America; North AmericaInformation provided by Lati Industria Termoplastici S.p.A.

Order this product through the following link:

http://www.lookpolymers.com/polymer_LATI-Lasulf-G15-PSU-15-Glass-Fiber-Reinforced.php

Physical Properties	Metric	English	Comments
Density	1.34 g/cc	0.0484 lb/in ³	
Linear Mold Shrinkage, Flow	0.0020 - 0.0045 cm/cm	0.0020 - 0.0045 in/in	
Linear Mold Shrinkage, Transverse	0.0065 - 0.0085 cm/cm	0.0065 - 0.0085 in/in	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	50.0 MPa	7250 psi	
	@Temperature 150 Â°C	@Temperature 302 Â°F	
	65.0 MPa	9430 psi	
	@Temperature 120 Â°C	@Temperature 248 Â°F	
	75.0 MPa	10900 psi	
	@Temperature 90.0 Â°C	@Temperature 194 Â°F	
	80.0 MPa	11600 psi	
	@Temperature 60.0 Â°C	@Temperature 140 Â°F	
	90.0 MPa	13100 psi	
	@Temperature 23.0 Â°C	@Temperature 73.4 Â°F	
Elongation at Break	2.3 %	2.3 %	
	@Temperature 150 Â°C	@Temperature 302 Â°F	
	2.4 %	2.4 %	
	@Temperature 90.0 Â°C	@Temperature 194 Â°F	
	2.4 %	2.4 %	
	@Temperature 120 Â°C	@Temperature 248 Â°F	
	2.5 %	2.5 %	

Mechanical Properties	Metric	English	Comments
	@Temperature 60.0 Â°C	@Temperature 140 Â°F	
	2.7 %	2.7 %	
	@Temperature 23.0 Â°C	@Temperature 73.4 Â°F	
Tensile Modulus	4.70 GPa	682 ksi	
	@Temperature 150 Â°C	@Temperature 302 Â°F	
	5.10 GPa	740 ksi	
	@Temperature 120 Â°C	@Temperature 248 Â°F	
	5.20 GPa	754 ksi	
	@Temperature 90.0 Â°C	@Temperature 194 Â°F	
	5.30 GPa	769 ksi	
	@Temperature 60.0 Â°C	@Temperature 140 Â°F	
	5.50 GPa	798 ksi	
	@Temperature 23.0 Â°C	@Temperature 73.4 Â°F	
Charpy Impact Unnotched	3.00 J/cmÂ²	14.3 ft-lb/inÂ²	
	@Temperature 23.0 Â°C	@Temperature 73.4 Â°F	
	4.00 J/cmÂ²	19.0 ft-lb/inÂ²	
	@Temperature -20.0 Â°C	@Temperature -4.00 Â°F	
Charpy Impact, Notched	0.350 J/cmÂ²	1.67 ft-lb/inÂ²	
	@Temperature 23.0 Â°C	@Temperature 73.4 Â°F	
	0.350 J/cmÂ²	1.67 ft-lb/inÂ²	
	@Temperature -20.0 Â°C	@Temperature -4.00 Â°F	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	160 Â°C	320 Â°F	
Deflection Temperature at 0.46 MPa (66 psi)	185 Â°C	365 Â°F	
Deflection Temperature at 1.8 MPa (264 psi)	175 Â°C	347 Â°F	

Thermal Properties <small>Heat Softening Point</small>	185 Â°C Metric	365 Â°F English	Comments
	@Load 5.00 kg	@Load 11.0 lb	
Flammability, UL94	V-1	V-1	
	@Thickness 1.50 mm	@Thickness 0.0591 in	
	V-0	V-0	
	@Thickness 3.00 mm	@Thickness 0.118 in	
Oxygen Index	35 %	35 %	
Glow Wire Test	960 Â°C	1760 Â°F	GWFI/GWT
	@Thickness 1.00 mm	@Thickness 0.0394 in	
	960 Â°C	1760 Â°F	GWFI/GWT
	@Thickness 2.00 mm	@Thickness 0.0787 in	

Electrical Properties	Metric	English	Comments
Comparative Tracking Index	125 V	125 V	A solution

Processing Properties	Metric	English	Comments
Melt Temperature	300 - 330 Â°C	572 - 626 Â°F	
Mold Temperature	120 - 140 Â°C	248 - 284 Â°F	
Drying Temperature	110 - 130 Â°C	230 - 266 Â°F	
	@Time 10800 sec	@Time 3.00 hour	

Descriptive Properties	Value	Comments
ISO Shrinkage - Pressure	60 MPa	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China