

## LATI Latamid 66 H2 G/35-V0HF1 PA 66, 35% Glass Fiber Reinforced, Heat Stabilized, Flame Retardant

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, 40% Glass Fiber Filled , Nylon 66, Glass Fiber Filled, Flame Retardant

### Material Notes:

Polyamide 66 (PA66) based compound. Heat stabilized. Glass fibers. UL94 V-0 classified, halogens-based flame retardants and red phosphorous free. Availability: Africa & Middle East; Asia Pacific; Europe; Latin America; North America Information provided by Lati Industria Termoplastici S.p.A.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_LATI-Latamid-66-H2-G35-V0HF1-PA-66-35-Glass-Fiber-Reinforced-Heat-Stabilized-Flame-Retardant.php](http://www.lookpolymers.com/polymer_LATI-Latamid-66-H2-G35-V0HF1-PA-66-35-Glass-Fiber-Reinforced-Heat-Stabilized-Flame-Retardant.php)

Physical Properties	Metric	English	Comments
Density	1.49 g/cc	0.0538 lb/in <sup>3</sup>	
Linear Mold Shrinkage, Flow	0.0035 - 0.0060 cm/cm	0.0035 - 0.0060 in/in	
Linear Mold Shrinkage, Transverse	0.0070 - 0.010 cm/cm	0.0070 - 0.010 in/in	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	160 MPa	23200 psi	
Elongation at Break	3.0 % @Temperature 23.0 Â°C	3.0 % @Temperature 73.4 Â°F	
Tensile Modulus	11.5 GPa	1670 ksi	
Charpy Impact Unnotched	7.00 J/cm <sup>2</sup>	33.3 ft-lb/in <sup>2</sup>	
Charpy Impact, Notched	0.880 J/cm <sup>2</sup>	4.19 ft-lb/in <sup>2</sup>	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	125 Â°C	257 Â°F	
Deflection Temperature at 0.46 MPa (66 psi)	255 Â°C	491 Â°F	
Deflection Temperature at 1.8 MPa (264 psi)	235 Â°C	455 Â°F	
Vicat Softening Point	245 Â°C @Load 5.00 kg	473 Â°F @Load 11.0 lb	
Flammability, UL94	V-0 @Thickness 3.00 mm	V-0 @Thickness 0.118 in	

Thermal Properties	Metric	English	Comments
	@Thickness 1.50 mm	@Thickness 0.0591 in	
	V-0	V-0	
	@Thickness 0.750 mm	@Thickness 0.0295 in	
Oxygen Index	32 %	32 %	
Glow Wire Test	775 Å°C	1430 Å°F	GWIT
	@Thickness 1.00 mm	@Thickness 0.0394 in	
	775 Å°C	1430 Å°F	GWIT
	@Thickness 2.00 mm	@Thickness 0.0787 in	
	960 Å°C	1760 Å°F	GWFI/GWT
	@Thickness 1.00 mm	@Thickness 0.0394 in	
	960 Å°C	1760 Å°F	GWFI/GWT
	@Thickness 2.00 mm	@Thickness 0.0787 in	

Electrical Properties	Metric	English	Comments
Comparative Tracking Index	600 V	600 V	A solution

Processing Properties	Metric	English	Comments
Melt Temperature	270 - 290 Å°C	518 - 554 Å°F	
Mold Temperature	70.0 - 100 Å°C	158 - 212 Å°F	
Drying Temperature	90.0 - 100 Å°C	194 - 212 Å°F	
	@Time 10800 sec	@Time 3.00 hour	

Descriptive Properties	Value	Comments
ISO Shrinkage - Pressure	60 MPa	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China